

HiDura™ MED AG33 NT0862

polyamide 66



HiDura MED AG33 NT is an injection moldable glass fiber reinforced PA66 resin designed for healthcare applications. It is characterized by excellent strength & stiffness for structural needs. The product is compliant to ISO 10993-5 and ISO 10993-10. It is very easy to color and exhibits good property retention after most sterilization methods.

General

Regional Availability	• North America	• Europe	• Asia Pacific
Additive	• Lubricant	• Release agent	
Features	• Bromine Free • Creep Resistant • Good Dimensional Stability • Good Mold Release • Halogen Content, None • High Tensile Strength • Solvent Resistant	• Chemical Resistant • Fatigue Resistant • Good Flow • Good Processability • High Rigidity • Homopolymer	• Corrosion Resistant • Good Colorability • Good Impact Strength • Good Stiffness • High Strength • Lubricated
Agency Rating	• BSE/TSE Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical

	dry	cond.	Unit	Test Standard
Density	1.4	-	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	0.9	*	%	
Flow : 23°C, 2.00 mm	0.4	*	%	
Water Absorption				ISO 62
23°C, 24 hr	0.8	*	%	
Equilibrium, 23°C, 50% RH	1.7	*	%	

Mechanical

	dry	cond.	Unit	Test Standard
Tensile Modulus (23°C)	10600	7900	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	205	145	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3	5	%	ISO 527-2
Flexural Modulus (23°C)	10200	6500	MPa	ISO 178
Flexural Strength (23°C)	290	200	MPa	ISO 178
Poisson's Ratio (23°C)	0.4		-	ISO 527-2

©2021 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

Impact	dry	cond.	Unit	Test Standard
Charpy Notched Impact Strength				ISO 179/1eA
+23°C	13	17	kJ/m ²	
-30°C	11	11	kJ/m ²	
-40°C	11	11	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
+23°C	86	100	kJ/m ²	
-30°C	71	77	kJ/m ²	
-40°C	69	75	kJ/m ²	
Notched Izod Impact Strength				ISO 180/1A
+23°C	12	16	kJ/m ²	
-30°C	10	12	kJ/m ²	
-40°C	10	11	kJ/m ²	

Thermal	dry	cond.	Unit	Test Standard
Heat Deflection Temperature				ISO 75-2/A
1.80 MPa, Unannealed	250	-	°C	
0.45 MPa, Unannealed	260	-	°C	
Melting Temperature	260	*	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C, 2.00 mm	21	*	E-6/K	
Transverse : 23 to 55°C, 2.00 mm	106	*	E-6/K	

Injection	Value	Unit
Drying Temperature	80	°C
Drying Time	4	h
Rear Temperature	280 - 310	°C
Middle Temperature	280 - 310	°C
Front Temperature	280 - 310	°C
Nozzle temperature	280 - 310	°C
Processing (Melt) Temperature	285 - 305	°C
Mold Temperature	65 - 95	°C

HiDURA™

North America
+1 888 927 2363

Europe
+32 10 608 600

Asia
+86 21 2315 0888

Disclaimer

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representation or warranties as to the completeness of accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purpose

©2021 Ascend Performance Materials Operations. The Ascend Performance Materials name, brands, marks and logos (e.g., those identified with ®, ™, or SM) are owned by Ascend Performance Materials Operations, unless otherwise noted.

HiDura™ MED AG33 NT0862

polyamide 66



prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting in the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representation or warranties, either express or implied, of merchantability fitness for a particular purpose or of any other nature are made hereunder with respect to information or product to which information refers.

CAUTION: Do not use Ascend Performance Materials Operations MED grades in medical applications involving implantation in the human body or contact with internal body fluids or tissues for extended periods of time.