

KYNAR SUPERFLEX[®]

2500-20 MED

Kynar Superflex[®] MED is a fluorinated thermoplastic copolymer.

The Superflex[®] MED has outstanding chemical resistance, imperviousness to UV, high barrier properties, high purity, good mechanical properties and is resistant to gamma, steam and ETO sterilization.

Moreover, this grade is flexible and suitable in medical tubing and film applications.

Kynar Superflex[®] 2500-20 MED is available in pellet form for extrusion, injection or compression. This product is tested for USP Class VI and ISO 10993 part 4 and part 5. Letters can be provided upon request.

PROPERTIES	VALUE	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	5.8	cm ³ /10min	ISO 1133
Temperature	232	°C	-
	450	°F	
Load	3.8	kg	-
	8.38	lb	
Melt Flow Rate	1 - 15	g/10min	ASTM D1238
Temperature	230	°C	-
Load	3.8	kg	-
Melt Viscosity, 230°C, 100 s-1	9 - 16	kPoise	ASTM D3835
MECHANICAL PROPERTIES			
Tensile Modulus	350	MPa	ISO 527-1/-2
	50800	psi	
Tensile Modulus, 73 °F	241 - 379	MPa	ASTM D638
	35000 - 55000	psi	
Yield stress	15	MPa	ISO 527-1/-2
	2180	psi	
Tensile Strength at Yield, 73 °F	11.7 - 19.3	MPa	ASTM D638
	1700 - 2800	psi	
Yield strain	18	%	ISO 527-1/-2
Elongation at Yield, 73 °F	17 - 25	%	ASTM D638
Nominal Strain at Break	>50	%	ISO 527-1/-2
Tensile Strength at Break, 73 °F	13.8 - 31	MPa	ASTM D638
	2000 - 4500	psi	
Elongation at Break, 73 °F	500 - 800	%	ASTM D638
Taber Abrasion, CS 17 1000g:pad	28 - 33	mg/1000 cycles	ASTM-G195-13A

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 17-01-2023

KYNAR SUPERFLEX[®]

2500-20 MED

Hardness, Shore D, 73 °F	50 - 57	-	ASTM D2240
Flexural Modulus, 73 °F	193 - 276	MPa	ASTM D790
	28000 - 40000	psi	
Flexural Strength @ 5% Strain, 73 °F	10.3 - 17.2	MPa	ASTM D790
	1500 - 2500	psi	
Compressive Strength, 73 °F	13.8 - 20.7	MPa	ASTM D695
	2000 - 3000	psi	
Charpy Notched Impact Strength, +23°C	No Break	kJ/m ²	ISO 179/1eA
Unnotched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Notched Impact Strength, 73 °F	No Break	kJ/m	ASTM D256
Coefficient of Friction, Static vs. Steel, 73 °F	0.49	-	ASTM D1894
Coefficient of Friction, Dynamic vs. Steel, 73 °F	0.54	-	ASTM D1894
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	122	°C	ISO 11357-1/-3
Melting Point, 73 °F	117 - 125	°C	ASTM D3418
Glass Transition Temperature, 10°C/min	-40	°C	ISO 11357-1/-2
Glass Transition Temperature (Tg)	-43.3 - -40	°C	ASTM D7028
	-46 - -40	°F	
Temp. of Deflection Under Load, 1.80 MPa	31	°C	ISO 75-1/-2
	88	°F	
Heat Deflection Temperature, 264 Psi, 248 °F/hr	26.7 - 37.8	°C	ASTM D648
	80 - 100	°F	
Coefficient of Thermal Expansion, 73 °F	15.3 - 19.4	10E-5/°C	ASTM D696
	8.5 - 10.8	10E-5/°F	
Burning Behav. at 1.5 mm Nominal Thickness	V-0	class	IEC 60695-11-10
Thickness Tested	1.5	mm	-
	0.0591	in	
Yellow Card available	yes	-	-
Burning Behav. at Thickness h	V-0	class	IEC 60695-11-10
Thickness Tested	1.0	mm	-
	0.0394	in	
Oxygen Index	44	%	ISO 4589-1/-2
Limiting Oxygen Index, 73 °F	42	%	ASTM D2863
Thermal Conductivity	0.144 - 0.18	W/(m K)	ASTM D433
	1 - 1.25	BTU in / (hr ft ² F)	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 17-01-2023

KYNAR SUPERFLEX[®]

2500-20 MED

Specific Heat	745 - 958 0.28 - 0.36	J/(kg K) BTU/(lb·°F)	DSC
Thermal Decomposition TGA, in air	375 707	°C °F	1% wt. loss
Thermal Decomposition TGA, in nitrogen	410 770	°C °F	1% wt. loss
ELECTRICAL PROPERTIES			
Dielectric Constant, 1 kHz	4.5 - 13.5	-	ASTM D150
Dissipation Factor, 100 kHz	0.05 - 0.29	-	ASTM D150
Volume Resistivity, DC 68 °F, 65% R.H.	2E14	Ohm*cm	ASTM D257
Surface Resistivity, 73 °F	8.5E11 - 9.2E11	Ohm per square	ASTM D257
Dielectric (Electric) Strength	12 305	kV/mm kV/in	IEC 60243-1
Dielectric (Electric) Strength, 73°F	0.8 - 1.1	kV/mil	ASTM D149
OTHER PROPERTIES			
Water Absorption	0.03	%	Sim. to ISO 62
Water Absorption	≤0.07	%	ASTM D570
Density	1790 1.79	kg/m ³ g/cm ³	ISO 1183
Specific Gravity, 73 °F	1.8 - 1.82	-	ASTM D792
OPTICAL PROPERTIES			
Refractive Index @ sodium D line	1.4	-	ASTM D542

PROCESSING Injection Molding, Sheet Extrusion, Coating, Transfer Molding	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 arkema.com Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
DELIVERY FORM Pellets	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 17-01-2023

KYNAR SUPERFLEX[®]

2500-20 MED

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.