POREX[®] Virtek[™] PTFE Materials

MD20

Parameters	Value	Unit of Measurement
BACTERIAL FILTRATION EFFICIENCY	>99.9999%	ASTM F2101 ¹ (nominal)
WATER ENTRY PRESSURE (WEP)	Min 350, Typical 550	mbar
AIR FLOW	Min 16, Typical 25	l/hr/cm² ∆p 70mbar
THICKNESS	0.25	mm (nominal)
THICKNESS	0.25	mm (nomina

Additional Information

- Can be supplied in format of:
 - Rolls (8mm-330mm width) on 75mm core -
 - Sheets
 - Discs -
- Assembly suggestions:
 - Ultrasonic welding
 - Thermal welding
 - Over-moulding
 - **Pressure Sensitive Adhesive**
 - Compression seal
- Sterilisation method:
 - Steam/Autoclave (repeated use)
 - EtO -
- Raw material is compliant with:
 - USP 28, NF 23, 2005, for USP Class VI Plastics at 70°C
 - FDA 21CFR 177,1550
 - PFOA Free, Compliant with (EC) No 1907/2006 REACH and Persistent Organic Pollutants (POP) EU 2019/1021
- ¹ ASTM F2101 was adapted to employ a more severe challenge. Test conditions and data available on request.

This standard sample is for evaluation of form, fit, and function to determine product specification requirements for custom products. Please reference the values in our data sheet for specification guidelines of standard products. In Vitro Diagnostic (IVD), medical-surgical and pharmaceutical samples are for investigational use only and subject to specific application, test condition and regulatory requirements.



CON002432 Rev 6.00

USA info.porex.us@filtrationgroup.com info.porex.europe@filtrationgroup.com info.porex.asia@filtrationgroup.com Tel: +1 770 964 1421 Fax: +1 770 969 0954

Porex Technologies GmbH Strangenhäuschen 30 52070 Aachen Germany

Tel: +49 241 9105250 Fax: +49 241 91052516 Porex Technologies Sdn Bhd Lot PT 74, Jln Hulu Tinggi 26/6, Sek. 26, Hicom Industrial Park, 40400 Shah Alam, Selangor, Malaysia

Tel: +603 51913308 Fax: +603 51923308



Porex Corporation

500 Bohannon Road

Fairburn, GA 30213