

PEBAX® 7033 SA 01 MED

Polyether block amide Pebax® 7033 SA 01 MED resin is a thermoplastic elastomer made of flexible polyether and rigid polyamide. This grade offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Pebax® 7033 SA 01 MED resin also offers an excellent combination of properties such as: kink resistance, low friction coefficient and superior dynamic response.

Upon request, letters regarding USP Class VI compliance can be provided.

Main applications:

- Tubings like angiography and angioplasty catheters.
- Flexible injected parts.

Packaging:

This grade is delivered dried in sealed packaging (20 kg bags) ready to be processed.

Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

MAIN CHARACTERISTICS

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
Molding shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5 / *	%	ISO 294-4, 2577
Tensile Modulus	60000 / 56600	psi	ISO 527-1/-2
Yield stress	3340 / 3190	psi	ISO 527-1/-2
Yield strain	22 / 20	%	ISO 527-1/-2
Nominal strain at break	>50 / >50	%	ISO 527-1/-2
Charpy impact strength, +23°C	- / N	ftlb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	- / N	ftlb/in ²	ISO 179/1eU
Charpy notched impact strength, +23°C	- / 57.1	ftlb/in ²	ISO 179/1eA
Charpy notched impact strength, -30°C	- / 9.51	ftlb/in ²	ISO 179/1eA
Melting temperature, 10°C/min	342 / *	°F	ISO 11357-1/-3
Vicat softening temperature, 50°C/h 50N	264 / *	°F	ISO 306
Water absorption	1.43 / *	%	Sim. to ISO 62
Humidity absorption	0.76 / *	%	Sim. to ISO 62
Density	1.01 / -	g/cm ³	ISO 1183
Injection Molding, melt temperature	500	°F	ISO 294
Injection Molding, mold temperature	140	°F	ISO 10724
Abrasion resistance	41 / *	mm ³	ISO 4649
Shore D hardness, 15s	61 / *	-	ISO 7619-1

Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 260°C / 290°C
- Typical mold temperature : 25 – 60°C

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

PEBAX® 7033 SA 01 MED

- **Drying time and temperature (only necessary for bags opened for more than two hours) : 5-7 hours at 70-80°C**

Processing conditions:

- **Typical melt temperature (Min / Recommended / Max) : 220°C / 235°C / 250°C.**

- **Drying time and temperature (only necessary for bags opened for more than two hours) : 5-7 hours at 70-80°C.**

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets

Special Characteristics

Light stabilized or stable to light, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/en/products/product-safety/disclaimer/index.html>

Pebax® is a registered trademark of Arkema
© 2019 Arkema Inc. All rights reserved.

pebax.com

Arkema Inc. – Technical Polymers

900 First Avenue
King of Prussia, PA 19406
Tel.: +1 610 205 7000
Fax: +1 610 205 7497
arkema-america.com

PEBAX®
BY ARKEMA

Headquarters: Arkema France

420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
Tel.: +33 1 49 00 80 80
Fax: +33 1 49 00 83 96
arkema.com